


International Series of Monographs in  
Analytical Chemistry, Volume 40

# Analytical Chemistry of Zirconium and Hafnium

**Anil K. Mukherji** Ph.D., D.Sc.

Chemistry Department, Drexel Institute of Technology, Philadelphia

**Pergamon Press**



*INTERNATIONAL SERIES OF MONOGRAPHS IN*  
**ANALYTICAL CHEMISTRY**

*General Editors:* R. BELCHER AND M. FRIESER

---

**VOLUME 40**

**ANALYTICAL CHEMISTRY OF**  
**ZIRCONIUM AND HAFNIUM**

This page intentionally left blank

# **ANALYTICAL CHEMISTRY OF ZIRCONIUM AND HAFNIUM**

BY

**ANIL K. MUKHERJI**

*Chemistry Department*

*Drexel Institute of Technology, Philadelphia, Pa*



**PERGAMON PRESS**

*Oxford · New York · Toronto*

*Sydney · Braunschweig*

Pergamon Press Ltd., Headington Hill Hall, Oxford  
Pergamon Press Inc., Maxwell House, Fairview Park, Elmsford, New York 10523  
Pergamon of Canada Ltd., 207 Queen's Quay West, Toronto 1  
Pergamon Press (Aust.) Pty. Ltd., 19a Boundary Street,  
Rushcutters Bay, N.S.W. 2011, Australia  
Vieweg & Sohn GmbH, Burgplatz 1, Braunschweig

Copyright © 1970 Pergamon Press Inc.

*All Rights Reserved. No part of this publication may be reproduced,  
stored in a retrieval system, or transmitted, in any form or by any  
means, electronic, mechanical, photocopying, recording or otherwise,  
without the prior permission of Pergamon Press Ltd.*

First edition 1970

Library of Congress Catalog Card No. 71-109236

*Printed in Great Britain by A. Wheaton & Co., Exeter*

08 006886 3

**TO JETU**

This page intentionally left blank

# CONTENTS

PREFACE	ix
PHYSICAL PROPERTIES OF ZIRCONIUM AND HAFNIUM	xi
1. <i>Aqueous Solutions of Zirconium and Hafnium</i>	1
2. <i>Dissolution of Ores and Alloys</i>	12
3. <i>Methods of Detection and Identification</i>	14
4. <i>Gravimetric Determinations</i>	18
5. <i>Titrimetric Methods</i>	45
6. <i>Electrometric Methods</i>	61
7. <i>Absorptiometric Methods</i>	74
8. <i>Separations Using Ion-Exchange</i>	100
9. <i>Separations Using Solvent Extraction</i>	128
10. <i>Separation of Hafnium from Zirconium</i>	157
11. <i>Spectrographic Analyses</i>	198
12. <i>X-ray Analyses</i>	226
13. <i>Neutron Activation Analysis and Separation of Tracers</i>	247
INDEX	273
OTHER TITLES IN THE SERIES	281



This page intentionally left blank

## PREFACE

ZIRCONIUM and hafnium have many interesting physical and mechanical properties such as corrosion resistance and mechanical strength of metals and alloys at both low and elevated temperatures. The transparency of zirconium to thermal neutrons has found its greatest use as a construction material in nuclear reactors. Hafnium is always associated with zirconium and their separation from each other remained a challenge to analytical chemists for several years. Hafnium has been used as control rods in nuclear reactors because of its large neutron cross-section. Less interest has been shown in the chemical and physical properties of hafnium through the years. This may, however, change as its applications widen. Hafnium can absorb and give up heat more than twice as fast as zirconium or titanium and seems very promising as a construction material for jet engines and space technology.

The monograph presents a collection and comparison of available literature on the characterization and analysis of zirconium and hafnium. The aqueous chemistry of zirconium and hafnium has been discussed to draw attention to the complications of hydrolysis and polymerization and their effect on analytical procedures. Classical methods such as gravimetric, titrimetric and absorptiometric are presented along with spectrographic, X-ray and neutron activation methods. Techniques for the separation, of zirconium from hafnium have been discussed. The monograph covers important literature up to 1967.

Thanks are due to Professor Henry Freiser for his valuable criticism of the manuscript.

*Philadelphia,  
Pennsylvania*

ANIL K. MUKHERJI

This page intentionally left blank

# PHYSICAL PROPERTIES OF ZIRCONIUM AND HAFNIUM

Property	Zirconium	Hafnium
Atomic number	40	72
Atomic weight	91.22	178.6
Atomic radius	1.452 Å	1.442 Å
Ionic radius (M <sup>4+</sup> )	0.74 Å	0.75 Å
Density	Close-packed hexagonal structure, 6.489 g/cm <sup>3</sup> (low hafnium) to 6.574 g/cm <sup>3</sup> (high hafnium); body-centered cubic high-temperature structure at 979°C, 6.046 g/cm <sup>3</sup>	13.09 ± 0.01 g/cm <sup>3</sup> at 20°C
Melting point	1852 ± 2°C	2222°C
Boiling point	3580°C	5400°C
Vapor pressure	1949–2054°K $\log P \text{ (atm)} = \frac{31,066}{T} + 7.3551$ $- 2.415 \times 10^{-4} T$	10 <sup>-10</sup> atm at 1867°C;  10 <sup>-9</sup> atm at 2007°C
Thermal expansion	Alpha, 5.85 × 10 <sup>-6</sup> per °C for heterogenously oriented polycrystals; body-centered cubic alpha, 9.7 × 10 <sup>-6</sup> per °C between 870 and 1337°C	Alpha phase, 0.000519 per °C between 20 and 200°C
Thermal expansion perpendicular to C-axis	Alpha, 6.96 × 10 <sup>-6</sup> per °C	—
Specific heat	At room temperature, 0.067 ± 0.001 cal/g °C; above 862°C, 0.08 cal/g °C	0.0351 cal/g °C between 25° and 100°C
Specific heat vs. temperature	Between 1.8° and 4.2°K, C <sub>p</sub> = 6.92 × 10 <sup>-4</sup> T + 464.5 (T/265) cal/mole/°C. C <sub>p</sub> = 0.070 + 3.6 × 10 <sup>-5</sup> T cal/g °C	—
Latent heat of fusion	5.5 kcal/mole (estimated)	—
Latent heat of vaporization	142,150 ± 350 cal/mole	—

PHYSICAL PROPERTIES OF ZIRCONIUM AND HAFNIUM—*cont.*

Property	Zirconium	Hafnium
Thermal conductivity	At 24°C—, 0.211 W/cm °C At 100°C—, 0.204 W/cm °C At 300°C—, 0.187 W/cm °C $K = 0.0308 (\rho - 0.00327)T + 0.0381$ , where $\rho$ is the electrical conductivity in reciprocal microhm-cm and $T$ is temperature in °K.	At 50°C, 0.233 W/cm °C
Electrical resistivity at room temperature	40 microhm-cm	35.1 microhm-cm
Temperature coefficient of electrical resistivity	$44 \times 10^{-4}$ per °C	0.0038 per °C
Electrochemical equivalent	Valence 4, 0.2363 mg/coulomb	Valence 4, 0.4626 mg/coulomb
Superconductivity critical temperature	0.546°K in zero magnetic field	—
Paramagnetic susceptibility	At 25°C, $1.3 \times 10^{-6}$ cgs At 700°C, $1.53 \times 10^{-6}$ cgs At 862°C, $1.9 \times 10^{-6}$ cgs	$0.42 \times 10^{-6}$ emu/g at 20°C
Thermal neutron cross-section	0.18 barns	105 barns
Ionization potential	34.33 eV for valence 3	—
Crystal structure	Close-packed hexagonal at 25°C; $a = 3.2312 \text{ \AA}$ $c = 5.1477 \text{ \AA}$ , $c/a = 1.5931 \text{ \AA}$ ; body-centered cubic at 862°C; $a = 3.6090 \text{ \AA}$	Close-packed hexagonal, alpha phase, $a = 3.1883 \text{ \AA}$ $c = 5.0422 \text{ \AA}$ ; body-centered cubic, beta phase, $a = 3.50 \text{ \AA}$ .
Modulus of elasticity	$13.7 \times 10^6$ psi	—
Hardness	87–98 B	100 B

## REFERENCES

1. LUSTMAN, B. and KERZE, K., JR., *The Metallurgy of Zirconium*, McGraw-Hill, N.Y., 1955.
2. BLUMENTHAL, W. B., *The Chemical Behavior of Zirconium*, Van Nostrand, N.Y., 1958.
3. *Mechanical Properties of Metals and Alloys*, National Bur. Standards, Circ. C447, 1943.

4. PEARSON, W. B., *A Handbook of Lattice Spacings and Structures of Metals and Alloys*, Pergamon Press, New York, 1958.
5. VAN ARKEL, A. E., *Reine Metalle*, J. Springer, Berlin, 1939.
6. RAYNAR, W. M., *Mining and Metallurgy*, **28**, 284 (1947).
7. MILLER, G. L., *Zirconium*, Academic Press, New York, 1957.
8. KIESS, C. C., *J. Res. Nat. Bur. Standards*, **56**, 167 (1956).
9. RAPPERPORT, E. J., *Acta Metallurgica*, **7**, 254 (1959).
10. ROTH, H. P., *Metal Progress*, **63**, 84 (1953).

This page intentionally left blank